

# UCB DATA SHEET

## Continuously Cast Iron

# UNIBAR 400-18LT

(EN-GJS-400-18C-LT, EN 16482)

GUIDANCE ONLY

### Characteristics

Offers superior machinability combined with good low temperature impact, fatigue, electrical conductivity and magnetic permeability, along with an increased ductility over 400-15. Noise and vibration damping are good in this grade. Conforms with EN-GJS-400-18C-LT (EN 16482).

### Size Range

UNIBAR STANDARD SIZES AND SUPPLY	
<b>Round</b>	25mm – 700mm
<b>Square</b>	25mm x 25mm – 550mm x 550mm
<b>Rectangle</b>	Up to 750mm x 550mm
<b>Supply condition</b>	As-cast, turned, peeled, milled and cut
<b>Length</b>	Standard 3080mm, other lengths available

### Chemistry

ELEMENT	TYPICAL %
<b>Carbon</b>	3.50 – 4.00
<b>Silicon</b>	1.70 – 2.30
<b>Manganese</b>	0.10 – 0.30
<b>Sulphur</b>	0.005 – 0.020
<b>Phosphorous</b>	0.015 – 0.08
<b>Magnesium</b>	0.04 – 0.07
<b>Others/Alloying</b>	Residual
<b>Iron</b>	Balance

Typical Ranges (Analysis at the discretion of UCB)

### Mechanical Properties

MATERIAL GRADE	MATERIAL SECTION mm	ANTICIPATED VALUES					MATRIX
		Tensile strength UTS N/mm <sup>2</sup> minimum	0.2% Proof Stress N/mm <sup>2</sup> minimum	Elongation % minimum	HB	Charpy impact Joules (Average of 3 tests at -20°C)	
Unibar 400-18LT	25 < D ≤ 60	400	240	18	120-180	12	Predominantly Ferritic
	60 < D ≤ 120	380	230	15		12	
	120 < D ≤ 400	360	220	12		10	
	400 < D ≤ 700+	360	220	12		10	


Taken from mid-radius of cast bar, not separately cast test bar.

### Brinell Hardness (HB)

Test 10mm dia Ball 3000Kg load depending on section size. Hardness readings are taken across the entire section of the bar. Hardness values for rectangles depend on the ratio of height to width and can be supplied upon request.

### Microstructure

Contains type V & VI nodular (spheroidal) graphite in accordance with ISO 945. The rim contains approximately 200/250 nodules/mm<sup>2</sup>, and is predominately ferritic (>95%), with the core containing 90/150 nodules/mm<sup>2</sup>. The core matrix is essentially ferritic with ≤5% pearlite. Chill carbides will be less than 5%, well dispersed.



(Photo 100x magnification)

### Heat Treat Response

Unibar 400-18LT is not recommended for hardening and tempering. The higher pearlitic grades Unibar 600-3 and 700-2 are more suitable.

### Grade colour code



### Density

7.3 g/cc